LUMILUX®

TECHNICAL DATA SHEET


50064 EFFECT GREEN SN-S

Product group: Long afterglow products according to DIN 67510 part 4

Primary use: Solvent-based paints and inks, thermoplastics, thermosetting plastics

TYPICAL LUMINESCENT PROPERTIES	
Excitation	White light and UV radiation
Colour of emission	Yellowish green (yG)

Typical excitation (left) and phosphorescence (right) spectra



Solstice

Typical intensity of afterglow according to the German standard DIN 67510-1[1]	after 2 minutes	968 mcd/m^2
	after 5 minutes	394 mcd/m^2
	after 10 minutes	160 mcd/m^2
	after 60 minutes	17 mcd/m^2
	after 120 minutes	7.1 mcd/m^2

Typical decal curve

NO DATA AVAILABLE

Reference criterion to DIN 67510, part 1 — min. 160/17-1178-W-K

TYPICAL CHEMICAL PROPERTIES	
Insoluble in	Alkalis, organic solvents
Decomposition by means of	Water, acids

TYPICAL PHYSICAL PROPERTIES	
Appearance	Yellow-green powder
Specific gravity	3.4 g/cm^3
Particle size distribution (COULTER Lasersizer 230)	35 µm (D_{50})

[1]Phosphorescent pigments and products. Measurement and marking at the producer

RESPONSIBLE CARE™
Driving Safety & Sustainability

All statements and information provided herein are believed to be accurate and reliable, but are presented without guarantee, warranty, or responsibility of any kind, express or implied. Statements regarding possible uses of our products are provided for informational purposes only and do not constitute a representation or warranty. Users remain responsible for evaluating all safety and environmental considerations. Any descriptions of future products, intended updates, or improved features or functions do not constitute a commitment by Solstice to develop, sell, or release such products, updates, features, or functions, as such decisions remain in our sole discretion.

For More Information Visit
solstice.com

Solstice Advanced Materials Inc.
115 Tabor Rd.
Morris Plains, NJ 07950

Solstice

146100-esm-tds-lumilux-effectgreen-sn-s-ltr-en | SOLS | Sept 2026
© 2026 Solstice Advanced Materials US, Inc.