


SOLSTICE

ACLAR[®] UltRx 6000

TECHNICAL DATA SHEET


Aclar[®] UltRx 6000 is a high transparent 6 mil (152 μ m) PCTFE homopolymer ultra-high moisture barrier film designed for semi-rigid and flexible film packaging applications for highly sensitive medicinal products in pharmaceutical and medical markets. This film is suitable for thermoforming and lamination to various substrates including PVC and PVC free solutions, such as PET, PP, and PE substrates for environmentally friendly applications.

PROPERTIES OF 6.0 MIL (152 μ m) FILM AT 73°F (23°C) - 50% RH		TYPICAL VALUE		TEST METHOD
		ENGLISH	METRIC	
Specific Gravity			2.11 g/cm ³	ASTM D1505
Yield		2,180 in ² /lb.	3.10 m ² /kg	
Haze		< 1 %		ASTM D1003
Crystalline Melting Point		412°F	211°C	ASTM D4591
Dimensional Stability	- MD	$\leq + 2 \%$		ASTM D1204
	(10 mins. @ 300°F/149°C) - TD	$\leq - 2 \%$		
Tensile Strength	- MD	4,000 - 7,000 psi	28 - 48 MPa	ASTM D882
	- TD	4,000 - 7,000 psi	28 - 48 MPa	
Elongation	- MD	150 - 225 %		ASTM D882
	- TD	150 - 225 %		
Modulus, secant	- MD	160,000 - 200,000 psi	1130 - 1379 MPa	ASTM D882
	- TD	160,000 - 200,000 psi	1130 - 1379 MPa	
Surface Tension (treated side)		≥ 42 dynes/cm		ASTM D2578
Oxygen Transmission Rate @ 73.4°F (23°C) / 50% RH		cc/100in ² dbar 0.59	cc/m ² dbar 9.14	ASTM F1927-20
Water Vapor Transmission Rate @ 77°F (25°C) / 60% RH @ 86°F (30°C) / 65% RH @ 104°F (40°C) / 75% RH @ 100°F (37.8°C) / 100% RH		g/100in ² d 0.0003	g/m ² d 0.0047	ASTM F1249
		0.0005	0.0078	
		0.0020	0.0302	
		0.0025	0.0380	



RESPONSIBLE CARE
OUR COMMITMENT TO SUSTAINABILITY

Although Solstice Advanced Materials Inc believes that the information contained herein is accurate and reliable, it is presented without guarantee or responsibility of any kind and does not constitute any representation or warranty of Solstice Advanced Materials Inc, either expressed or implied. A number of factors may affect the performance of any products used in conjunction with user's materials, such as other raw materials, application, formulation, environmental factors and manufacturing conditions among others, all of which must be taken into account by the user in producing or using the products. The user should not assume that all necessary data for the proper evaluation of these products are contained herein. Information provided herein does not relieve the user from the responsibility of carrying out its own tests and experiments, and the user assumes all risks and liabilities (including, but not limited to, risks relating to results, patent infringement, regulatory compliance and health, safety and environment) related to the use of the products and/or information contained herein



For More Information Visit

solstice.com

Solstice Advanced Materials Inc.

115 Tabor Rd. | Morris Plains, NJ 07950



© 2026 Solstice Advanced Materials Inc.

6773800 | Aclar UltRx 6000 EN | Data Sheet | 441 DPH | 04.2026