

HYDROBLOCK® P-SERIES TR FILM

Hydroblock® P-series TR film is a poly-chloro-tri-fluoroethylene homopolymer, high performance barrier film for industrial and electronics applications. It provides outstanding water vapor barrier and excellent chemical resistance with high clarity.

COMPARISON OF TYPICAL PROPERTIES		P600TR	P800TR	P900TR
Thickness		0.6 mil	0.8 mil	0.9 mil
Yield		21,896 in ² /lb.	16,420 in ² /lb.	14,595 in ² /lb.
Haze			<1%	
Crystalline Melting Point			412°F	
Dimensional Stability 300°F/10 min.	MD	≤ +12%	≤ +12%	≤ +12%
	TD	≤ -12%	≤ -12%	≤ -12%
Tensile Strength	MD	11,000 - 17,000 psi	11,000 - 16,000 psi	11,000 - 16,000 psi
	TD	5,500 - 7,000 psi	6,000 - 7,200 psi	6,000 - 7,200 psi
Elongation	MD	80-130%	100-150%	100-150%
	TD	200-275%	200-275%	200-275%
Modulus, Secant	MD	200,000 - 240,000 psi	190,000 - 225,000 psi	190,000 - 225,000 psi
	TD	220,000 psi	165,000 - 210,000 psi	165,000 - 210,000 psi
Tear Strength, Graves	MD	0.6 lbf	0.9 lbf	1.0 lbf
	TD	0.6 lbf	0.9 lbf	1.0 lbf
Water Vapor Transmission Rate 100°F /100% RH		0.027 gms/100in ² /day	0.021 gms/100in ² /day	0.017 gms/100in ² /day

COMPARISON OF TYPICAL PROPERTIES		P2000TR	P3000TR	P4000TR	P6000TR
Thickness		2 mil	3 mil	4 mil	6 mil
Yield		6,567 in ² /lb.	4,380 in ² /lb.	3,285 in ² /lb.	2,180 in ² /lb.
Haze				<1%	
Crystalline Melting Point				412°F	
Dimensional Stability 300°F/10 min.	MD	≤ +6%	≤ +6%	≤ +5%	≤ +3%
	TD	≤ -6%	≤ -6%	≤ -5%	≤ -3%
Tensile Strength	MD	7,000 - 10,000 psi	6,000 - 9,000 psi	5,000 - 6,000 psi	5,000 - 6,000 psi
	TD	4,500 - 7,500 psi	4,000 - 7,000 psi	5,000 - 6,000 psi	5,000 - 6,000 psi
Elongation	MD	150-200%	150-225%	150-225%	150-225%
	TD	175-250%	175-225%	175-250%	100-200%
Modulus, Secant	MD	170,000 - 200,000 psi	170,000 - 200,000 psi	175,000 - 225,000 psi	175,000 - 225,000 psi
	TD	170,000 - 200,000 psi	170,000 - 200,000 psi	175,000 - 225,000 psi	175,000 - 225,000 psi
Tear Strength, Graves	MD	2.2 lbf	3.3 lbf	4.2 lbf	6.3 lbf
	TD	2.2 lbf	3.3 lbf	4.2 lbf	6.3 lbf
Water Vapor Transmission Rate 100°F /100% RH		0.0084 gms/100in ² /day	0.0064 gms/100in ² /day	0.0040 gms/100in ² /day	0.0027 gms/100in ² /day



All statements and information provided herein are believed to be accurate and reliable, but are presented without guarantee, warranty, or responsibility of any kind, express or implied. Statements regarding possible uses of our products are provided for informational purposes only and do not constitute a representation or warranty. Users remain responsible for evaluating all safety and environmental considerations. Any descriptions of future products, intended updates, or improved features or functions do not constitute a commitment by Solstice to develop, sell, or release such products, updates, features, or functions, as such decisions remain in our sole discretion. © 2026 Solstice Advanced Materials US, Inc.



For More Information Visit
solstice.com

Solstice Advanced Materials Inc.
115 Tabor Rd. | Morris Plains, NJ 07950



© 2026 Solstice Advanced Materials US, Inc.
7120003-esm-tds-hydroblock-tr-ltr-en | SOLS | 07/26