

A-C® WAXES FOR PVC PROFILE EXTRUSION

In profile extrusion, A-C® polyethylene waxes can provide increased output rates, reduced calibration plate-out, controlled fusion maintaining physical properties and enhanced surface quality.



PROPERTIES


PRODUCT	A-C GA	A-C 617A	A-C 629A	A-C 680A	A-C 316A	A-C 400A
Type of polyethylene wax	Low-density homopolymers		Oxidized low density homopolymers		Oxidized high density homopolymers	Ethylene vinyl acetate copolymer
Drop point (°C)	106	102	101	108	140	92
Viscosity (cps 140°)	375	180	200	250	8500 (150°C)	595
Acid number (mg KOH/g)	0	0	15	16	16	13% vinyl acetate
Density (g/cm³)	0.92	0.91	0.93	0.93	0.98	0.92
Dosage (phr)	0.1-0.4		0.1-0.4		0.05-0.2	0.1-0.4

BENEFITS

PRODUCT	PERFORMANCE IN PVC PROFILE EXTRUSION
A-C 6A A-C 16A A-C 617A	Excellent external lubrication providing enhanced gloss and surface quality; delay fusion
A-C 629A A-C 680A	Best combination of external lubrication and fusion control, providing metal release
A-C 316A	Superior additives for metal release; highly efficient fusion promoter enabling controlled pressure build up in the extruder; excellent distribution of additives resulting in increased melt homogeneity; reduced gloss
A-C 400A	Excellent external lubrication providing enhanced gloss and surface quality; relatively neutral to fusion. Reduce chattering in calibration unit and reduce melt pressure



Although Solstice Advanced Materials believes that the information contained herein is accurate and reliable, it is presented without guarantee or responsibility of any kind and does not constitute any representation or warranty of Solstice Advanced Materials, either expressed or implied. A number of factors may affect the performance of any products used in conjunction with user's materials, such as other raw materials, application, formulation, environmental factors and manufacturing conditions among others, all of which must be taken into account by the user in producing or using the products. The user should not assume that all necessary data for the proper evaluation of these products are contained herein. Information provided herein does not relieve the user from the responsibility of carrying out its own tests and experiments, and the user assumes all risks and liabilities (including, but not limited to, risks relating to results, patent infringement, regulatory compliance and health, safety and environment) related to the use of the products and/or information contained herein.



For More Information, [Click Here](#)
or Scan the QR Code

Solstice Advanced Materials Inc.
115 Tabor Rd. | Morris Plains, NJ 07950



© 2026 Solstice Advanced Materials Inc.
2000-05-ESM-TDS-AC-Wax-PVCProfile | SOLS | 04/26