

SOLSTICE A-C™ POLYMERS FOR METALLOCENE HOT MELT ADHESIVES

Solstice A-C low-molecular-weight polymers help boost the adhesion performance of metallocene-based hot melt adhesives, particularly in packaging application



INCREASED HEAT RESISTANCE



Adhesive performance at high temperatures is critical to ensuring that the quality of the packaging does not degrade over its useful life. The graph shows a significant increase in shear adhesion failure temperature when A-C polymers are added to metallocene hot melt adhesives.

TEST COMPOSITION (%)	CONTROL	A-C
A-C Low MWPE	0	7.5
HC Tackifier	30	30
Metallocene polymer	40	40
FT Wax	30	22.5

INCREASED ADHESION


Adding A-C polymers to metallocene hot melt adhesives will result in increased fiber tear on coated cardboard in packaging applications, even under refrigerator and freezer temperatures

Shear Adhesion Failure Temperature



REDUCED SET TIME

Adding A-C performance polymers to metallocene hot melt adhesive formulations will reduce the set time. Generally, Fischer-Tropsch waxes are used to achieve reduced set times. Using A-C polymers with or without Fischer-Tropsch waxes will provide reduced set times, as well as the additional benefits of increased adhesion and heat resistance.



SELECTION OF RECOMMENDED PRODUCTS

	TYPE	BENEFITS	DROP POINT (°C)	HARDNESS (DMM)	DENSITY	VISCOSITY AT 140 °C (CPS)
A-C 6	Homopolymer PE	Reduced set time and increased heat resistance	106	4	0.92	375
A-C 9	Homopolymer PE	Reduced set time and increased heat resistance	115	0.5	0.93	450
A-C 820	Homopolymer PE	Reduced set time and increased heat resistance	126	<0.5	0.96	80
A-C 573P	Maleated PE	Increased adhesion	106	4.5	0.92	600
A-C 596P	Maleated PP	Increased adhesion and increased heat resistance	141	<0.5	0.93	150 (190 °C)
A-C 597P	Maleated PP	Increased adhesion and increased heat resistance	141	<0.5	0.94	350 (190 °C)



All statements and information provided herein are believed to be accurate and reliable, but are presented without guarantee, warranty, or responsibility of any kind, express or implied. Statements regarding possible uses of our products are provided for informational purposes only and do not constitute a representation or warranty. Users remain responsible for evaluating all safety and environmental considerations. Any descriptions of future products, intended updates, or improved features or functions do not constitute a commitment by Solstice to develop, sell, or release such products, updates, features, or functions, as such decisions remain in our sole discretion. © 2026 Solstice Advanced Materials US, Inc.



For More Information Visit

solstice.com

Solstice Advanced Materials Inc.

115 Tabor Rd. | Morris Plains, NJ 07950



© 2026 Solstice Advanced Materials US, Inc.

67700 | Hot Melts | BRO | July + 2026